



### Pine SNÖHETTA

(picture always a reference, sample must be ordered)

### Wood Species

A typical feature for pine is the big part of heartwood. By time the heartwood makes the outlook of pine reddish. The sapwood stays lighter. As floor material pine has a long tradition and the natural aging of pine is impossible to copy. Pine is ideal for peaceful and private locations. Knottiness is a typical feature of pine. As a floor, pine is ideal for summer houses and locations with light traffic.

Brinell ~ 1,9 HB

Density, airdry 510 kg / m<sup>3</sup>

### GRADE

Pine has only one grade, Natural grade. Pine Natural grade is characterized by knots. The variety is allowed to have healthy black knots, filled knots, round knots, and mustache knots.

NOTE! The surface treatment may affect the appearance and tone of the painted area.

### PRODUCT MEASUREMENTS

- Thickness: **14,0 mm**
- Width: **185 mm**
- Length: 1818 / 2000 / 2080 / **2180 mm** (one length/package)
- Surface: 3,0 mm
- Weight: 10 kg/m<sup>2</sup>

### STRUCTURE

- Single plank wooden floor
- 0,7 mm micro bevel on the long sides
- 0,5 mm micro bevel on the short side
- 3-layer cross-glued structure:
  - Surface layer 3,0 mm
  - Middle layer Finnish birch plywood
  - Counter balance veneer Finnish spruce 2 mm

### SURFACE TREATMENT

- UV hardened wax oil
- Brushed surface


### INSTALLATION OPTIONS

- Floating installation (with underlay material) or glued down to subfloor (concrete or plywood)
- Locking system WiseLoc / Traditional Tongue and Groove
- Suitable with underfloor heating



### QUALITY

- FINNISH quality work - produced from beginning to end in Finland
- ALLERGY LABEL - only wooden flooring certified by Finnish Allergy, Skin and Asthma Federation
- PEFC - wooden raw material comes from certified and sustainably managed forests
- JAS2 - Japanese glue seam standard, tolerates the boiling test
- JAS F\*\*\*\* - the highest formaldehyde standard in the world, Timberwise uses the formaldehyde free EPI glue
- M1 - Finnish Building material emission standard
- For lacquered products fire classification Bfl-Is available on request
- Antibacterial treatment available on request



# Pine SNÖHETTA

(picture always a reference, sample must be ordered)





